

## ABSTRACT

The invention relates to a process for producing mouldings by injection moulding, the steps in the process being

A) Melting a mixture made from

- a) a (meth)acrylate copolymer composed of from 40 to 100% by weight of free-radical-polymerized C<sub>1</sub>-C<sub>4</sub>-alkyl esters of acrylic or methacrylic acid and from 0 to 60% by weight of (meth)acrylate monomers having an anionic group in the alkyl radical, where the copolymer comprises
  - b) from 0.1 to 3% by weight of a release agent,
- and, where appropriate, the mixture may comprise
- c) from 0 to 50% by weight of a drier,
  - d) from 0 to 30% by weight of a plasticizer,
  - e) from 0 to 100% by weight of additives or auxiliaries,
  - f) from 0 to 100% by weight of an active pharmaceutical ingredient,
  - g) from 0 to 20% by weight of another polymer or copolymer,

where the amounts given for components b) to g) are based on the (meth)acrylate copolymer a) and the mixture prior to melting has a content of more than 0.5% by weight of low-boiling constituents with vapour pressure of at least 1.9 bar at 120°C,

094320 03101

B) Devolatilizing the mixture in the thermoplastic state at temperatures of at least 120°C, thereby lowering to not more than 0.5% by weight the content of the low-boiling constituents with vapour pressure of at least 1.9 bar at 120°C,

C) Injecting the molten and devolatilized mixture into the mould cavity of an injection mould, the temperature of the mould cavity being below the glass transition temperature of the (meth)acrylate copolymer by at least 10°C, cooling the molten mixture, and removing the resultant moulding from the mould.

0913720 003101